

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Petr. Corp.</i>		Lease <i>Dayton E/</i>		Well # <i>1</i>	
Location of Well	Unit <i>P 9905+E</i>	Section <i>21</i>	Township <i>18</i>	Range <i>26</i>	County <i>Eddy</i>
Drilling Contractor <i>Byrd Drilling Co</i>			Type of Equipment <i>Rotary</i>		

* witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>15"</i>	<i>10 3/4"</i>	<i>32</i>		<i>400</i>	<i>Circ.</i>
<i>9 1/2"</i>	<i>7"</i>	<i>20 23 #</i>		<i>1240</i>	<i>Circ.</i>
<i>6 1/4"</i>	<i>4 1/2" + 5 1/2"</i>	<i>9.5 + 15.5</i>		<i>1800</i>	<i>150</i>

Casing Data:

7 1/2" Surface *51* joints of *7* inch *23* # Grade *API* *10-5-55*
(Approved) (Rejected)

Inspected by *L. L. Williams* date *12-21-75*

Cementing Program

Size of hole *9 1/4"* Size of Casing *7* Sacks cement required *500*

Type of Shoe used *Tool Joint* Float collar used *None* Btm *2* jts welded *Thread Lock*

TD of hole *1210' 10"* Set *1177'* Feet of *27* Inch *23* # Grade *5-55*

New-used csg. @ *1177'* with *150* sacks neat cement around shoe *Class C 4200*
+ *350* sack *Class C* additives *6 1/2* lb *Aluminate* *6 1/2* lb *Iron* *2 1/2* lb

Plug down @ *1210'* (AM) (PM) Date *12-21-75*

Cement circulated *700* No. of Sacks *50/100*

Cemented by *Deaton* Witnessed by *L. L. Williams*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *Surface* TD *426' 10"* *413' 30"* *15" 106'* *10 1/4"*

10 1/4" *32* # *API* *H-40*, *at 2500'p* *Class C 4200*

TD 2100' 10" *12-24-75* *Circ 50/100*