

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Petr. Corp.</i>		Lease <i>Dayton FO</i>		Well # <i>1</i>	
Location of Well	Unit <i>F</i>	Section <i>28</i>	Township <i>18</i>	Range <i>26</i>	County <i>Eddy</i>
Drilling Contractor	<i>Byrd Drilling Co.</i>		Type of Equipment <i>Rotary</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>15"</i>	<i>10 3/4"</i>	<i>32</i>		<i>400</i>	<i>air</i>
<i>9 1/2"</i>	<i>7"</i>	<i>20</i>		<i>1200</i>	<i>"</i>
<i>6 1/4"</i>	<i>4 1/2 + 5 1/2"</i>	<i>9.5 + 15.5</i>		<i>1900</i>	<i>150</i>

Casing Data:

Surface *31* joints of *7* inch *20* # Grade *API New K-55*
(Approved) (Rejected)

Inspected by *Alan Mermin* date *2-16-76*

Cementing Program

Size of hole *9 1/2"* Size of Casing *7* Sacks cement required *500*

Type of Shoe used *Sub Tool* Float collar used *None* Btm *2* jts *noted* *Thread lock*

TD of hole *1165' KB Set 1152' 6"* Feet of *7* Inch *20* # Grade *K-55*

New-used csg. @ *1152' 6"* with *150* sacks neat cement around shoe class *C* *2% cc*
+ *350* sack *Class C* additives *6% Bilonite 6% Flocc 2% cc*

Plug down @ *10:30* (AM) (PM) Date *2-16-76*

Cement circulated *Yes* No. of Sacks *25*

Cemented by *Denton* Witnessed by *Alan Mermin*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *Spud 2:00 PM 2-14-76*

Water 103-280, 318-450, 460-600