

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Llano Inc</u>		Lease <u>Leavitt</u>		Well # <u>1</u>	
Location of Well	Unit <u>F</u>	Section <u>13</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>1980 FNL 1650 FNL</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>20"</u>	<u>16"</u>	<u>65</u>		<u>200'</u>	<u>250' Cigs</u>
<u>15"</u>	<u>11 3/4"</u>	<u>42</u>		<u>950'</u>	<u>350</u>
<u>10 1/2"</u>	<u>8 3/4"</u>	<u>24</u>		<u>1950'</u>	<u>500 "</u>
<u>7 3/8"</u>	<u>4 1/2"</u>	<u>10.5, 11.6</u>		<u>9300</u>	<u>450</u>

Casing Data:

Int Surface 23 joints of 11 3/4 inch 42 # Grade H-40 New APT
(Approved) (~~Rejected~~)

Inspected by Lelan Mermis date 4-6-76

Cementing Program

Size of hole 15" Size of Casing 11 3/4 Sacks cement required 550

Type of Shoe used Guide Float collar used Insert Btm 2 jts welded Thread Lock

TD of hole 950' KB Set 940' GL Feet of 11 3/4 Inch 42 # Grade H-40

New-used csg. @ 940' GL with 200 sacks neat cement around shoe Class C 2% cc
+ 350 sax Nasco 2 lb additives 5" Gibbsite 4" Flocc 2% cc

Plug down @ 1800 (AM) (PM) Date 4-8-76

Cement circulated Yes No. of Sacks 15/54

Cemented by Halliburton Witnessed by Lelan Mermis

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Surface 20" hole Ran 5 jts 16" 65" TD 195' KB set at

185' GL Guide shoe Ant 150/5x Class C 2% cc 2% cc, 700/5x

Class C 2% cc PD 12:00 Midnight 4-6-76, Circ a show

of Ant and fell back, Filled hole to surface w/ 3 yds Ready Mix

Water 95-100, 225-520, 656-75, 718-70