

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates</u>		Lease <u>Cannon FW</u>		Well # <u>2</u>	
Location of Well	Unit <u>E</u> <u>2310 N</u> <u>990 W</u>	Section <u>21</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor <u>Byrd & Co.</u>			Type of Equipment <u>Rotary</u>		

Witness APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>15</u>	<u>10 3/4</u>	<u>32</u>		<u>400</u>	<u>line</u>
<u>9 1/2</u>	<u>7"</u>	<u>20-23 #</u>		<u>1200</u>	<u>line</u>
<u>6 1/4</u>	<u>4 1/2 + 5 1/2"</u>	<u>9.5 + 15.5</u>		<u>1900</u>	<u>150</u>

Casing Data:

Surface 30 joints of 7 inch 20 # Grade API New K-55
(Approved) (Rejected)

Inspected by De la Can Mermin date 4-26-76

Cementing Program

Size of hole 9 1/2 Size of Casing 7 Sacks cement required 500/50

Type of Shoe used True Plug Float collar used None Btm 2 jts welded Thread Lock

TD of hole 1220' KB Set 1206' Feet of 7 inch 20 # Grade K-55

New-used csg. @ 1206' with 150 sacks neat cement around shoe Class C 28 cc
+ 350 sax Class C additives 6% Gilsomite 6% Fluocel 2% cc

Plug down @ 4:15 (AM) (PM) Date 4-27-76

Cement circulated Yes No. of Sacks 20/50

Cemented by Denton Witnessed by De la Can Mermin

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Conc 1177 & 688 Buckets 729, 646

Water 124'-52', 346'-750', 1102'-1120'