

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Grates Ref. Corp.</u>		Lease <u>Dayton FI</u>		Well # <u>2</u>	
Location of Well	Unit <u>990N 330E</u>	Section <u>28</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>Byrd Drilling Co.</u>		Type of Equipment <u>Rotary to start 9-7-76</u>		

* APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>15"</u>	<u>10 3/4"</u>	<u>32</u>		<u>400</u>	<u>Circ.</u>
<u>9 7/8"</u>	<u>7"</u>	<u>20</u>		<u>1230'</u>	<u>"</u>
<u>6 1/4"</u>	<u>4 1/2" + 5 1/2"</u>	<u>9.5 + 15.5</u>		<u>1800'</u>	<u>"</u>

Casing Data:

Surface 38 joints of 7 inch 23 # Grade used API N-80
(Approved) (Rejected)

Inspected by Lelan Mearns date 9-9-76

Cementing Program

Size of hole 9 7/8" Size of Casing 7 Sacks cement required 500/sx

Type of Shoe used Texas A&N Float collar used None Btm 3 jts welded Thread Lock

TD of hole 1211' KB Set 1198' GL Feet of 7 Inch 23 # Grade N-80

New-used csg. @ 1198' GL with 150 sacks neat cement around shoe Class C 2% cc
+ 350 sax Class C additives 6 # Gilonite 1/2" Floccle 2% cc

Plug down @ 1100 (AM) (PM) Date 9-10-76

Cement circulated Yes No. of Sacks 25/sx

Cemented by Denton Witnessed by Lelan Mearns

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Water 125-656 887-92