

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Gates Petr. Corp.</u>		Lease <u>7th G4</u>		Well # <u>1</u>	
Location of Well	Unit <u>4505</u> <u>3102</u>	Section <u>22</u>	Township <u>18</u>	Range <u>26</u>	County <u>Elly</u>
Drilling Contractor	<u>Byrd</u> <u>Daly Co.</u>		Type of Equipment <u>Petrol to start</u> 10-13-76		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>15</u>	<u>10 3/4</u>	<u>32</u>		<u>400</u>	<u>lin.</u>
<u>9 1/2</u>	<u>7"</u>	<u>20</u>		<u>1200</u>	<u>lin.</u>
<u>6 1/4</u>	<u>4 1/2 + 5 1/2</u>	<u>10.5 + 15.5</u>		<u>1800</u>	<u>150</u>

Casing Data:

Surface 36 joints of 7" inch 20 # Grade used API J-55
(Approved) (Rejected)

Inspected by Selan Mermis date 10-17-76

Cementing Program

Size of hole 9 1/2" Size of Casing 7" Sacks cement required 500/sx

Type of Shoe used Guide Float collar used None Btm 2 jts welded Thread Lock

TD of hole 1165' KB Set 1152' Feet of 7" Inch 20 # Grade J-55

New-used csg. @ 1152' GL with 150/ sacks neat cement around shoe Class C 2% cc
+ 350 sax Class C Mix additives 5% Gilsomite 1/4% Floccle 2% cc

Plug down @ 10:30 (AM) (PM) Date 10-17-76

Cement circulated Yes No. of Sacks 25

Cemented by Denton Witnessed by Selan Mermis

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Water 67-190, 212-68, 374-82, 400-730, 960-64