

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Gates Petr. Corp.</u>		Lease <u>Gulf BZ</u>		Well # <u>1</u>	
Location of Well	Unit <u>H</u> <u>2310N</u> <u>330E</u>	Section <u>28</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>Byrd & Co.</u>		Type of Equipment <u>Rotary to start cement 11-30-76</u>		
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>9 1/2"</u>	<u>7"</u>	<u>20</u>		<u>1200</u>	<u>500 ctn.</u>
<u>6 1/4"</u>	<u>4 1/2 + 5 1/2"</u>	<u>10.5 + 15.5</u>		<u>1850</u>	<u>175 "</u>
Casing Data:					
Surface <u>25</u> joints of <u>7</u> inch <u>20</u> # Grade <u>API New K-55</u>					
(Approved) (Rejected)					
Inspected by <u>Selan Merriam</u> date <u>1-16-77</u>					
Cementing Program					
Size of hole <u>9 1/2"</u> Size of Casing <u>7"</u> Sacks cement required <u>500/54</u>					
Type of Shoe used <u>Guide</u> Float collar used <u>None</u> Btm <u>2</u> jts <u>welded</u> <u>Thread-LOCK</u>					
TD of hole <u>1155' KB</u> Set <u>1141' GL</u> Feet of <u>7</u> inch <u>20</u> # Grade <u>K-55</u>					
New-used csg. @ <u>1141' GL</u> with <u>150</u> sacks neat cement around shoe <u>Class C 2% CC</u>					
+ <u>350</u> /sax <u>Class C mix</u> additives <u>6" Gilsonite</u> <u>1/2" Flocc</u> <u>2% CC</u>					
Plug down @ <u>7:20</u> (AM) (PM) Date <u>1-17-77</u>					
Cement circulated <u>Yes</u> No. of Sacks <u>20/54</u>					
Cemented by <u>Denton</u> Witnessed by <u>Selan Merriam</u>					
Temp. Survey ran @ (AM) (PM) Date top cement @					
Casing test @ (AM) (PM) Date					
Method Used Witnessed by					
Checked for shut off @ (AM) (PM) Date					
Method used Witnessed by					
Remarks: <u>Water 125-600, 886-92</u>					