

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Patco Petr. Corp.</i>		Lease <i>Jayne H G</i>		Well # <i>1</i>	
Location of Well	Unit ^P <i>99054e</i>	Section <i>22</i>	Township <i>18</i>	Range <i>26</i>	County <i>Eddy</i>
Drilling Contractor	<i>Byrd Pugh &</i>		Type of Equipment <i>Rotary</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>9 1/2"</i>	<i>7"</i>	<i>20</i>		<i>1200'</i>	<i>500 ccs.</i>
<i>6 1/4"</i>	<i>4 1/2 + 5 1/2"</i>	<i>10.5 + 15.5</i>		<i>1900</i>	<i>150 ccs.</i>

Casing Data:

Surface 27 joints of 7 inch 20 # Grade K-55, Rge 3, 8rd
☒ (Approved) ☐ (Rejected)

Inspected by Mike Williams date 1-29-77

Cementing Program

Size of hole 9 1/2 Size of Casing 7 Sacks cement required 500

Type of Shoe used ^{Halliburton} Guide Float collar used — Btm 3 jts welded Yes

TD of hole 1202 Set ^{KB} 1215 Feet of 7 Inch 20 # Grade K-55

~~New~~ used csg. @ 1202 with 150 sacks neat cement around shoe 1 1/2 % CC
 + 350 sack Tincor additives 6 # Gilsinite - 1/4" Floseal - 2 % CC

Plug down @ 4:30 (AM) (PM) Date 1-30-77

Cement circulated Yes No. of Sacks 10

Cemented by George Denton Witnessed by Mike Williams

Temp. Survey ran @ — (AM) (PM) Date — top cement @ —

Casing test @ — (AM) (PM) Date —

Method Used — Witnessed by —

Checked for shut off @ — (AM) (PM) Date —

Method used — Witnessed by —

Remarks:

Cement fell back to 38' Filled hole w/ 3 yards of redi-mix

Centralizers @ 592 + 1182

Baskets @ 628 + 552

Drilling Breaks @ 263-68, 374-76, 515-35, 575-652, 677-87