

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Markab Energy Corp.</u>		Lease <u>Shirley</u>		Well # <u>1</u>	
Location of Well	Unit <u>6603 1980W</u>	Section <u>35</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>Pennsylvania & Co.</u>		Type of Equipment <u>Pottery</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>10</u>	<u>7"</u>	<u>20</u>		<u>920</u>	<u>cin.</u>
<u>6 1/4</u>	<u>4 1/2"</u>	<u>10.5</u>		<u>1250</u>	<u>250 cin.</u>

Casing Data:

Surface 29 joints of 7" inch 26 # Grade API Used N-80 LTRC
(Approved) (~~Rejected~~)

Inspected by Lelan Mermin date 10-20-77

Cementing Program

Size of hole 9 1/2" Size of Casing 7" Sacks cement required 310/sx

Type of Shoe used Float Float collar used no Btm 3 jts ~~welded~~ Threadlock

TD of hole 906' 6" Set 906' 6" Feet of 7" Inch 26 # Grade N-80

New-used csg. @ 906' 6" with 125 sacks neat cement around shoe Class C 2 1/2 cc
+ 185/sax Hance Lite additives 5# Gisonite 1/4# Flocele 2 1/2 cc

Plug down @ 1:20 (AM) (PM) Date 10-21-77

Cement circulated Yes No. of Sacks a trace

Cemented by Hallibarton Witnessed by Lelan Mermin

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Circ a trace of ant and fell back slow. Hole will be filled w/ Ready-mix.