

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Amoco Prod. Co.</u>		Lease <u>Johnson</u>		Well # <u>1</u>	
Location of Well	Unit <u>H</u> <u>1989 1/2</u>	Section <u>10</u>	Township <u>18</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor			Type of Equipment <u>Rotary Drilling approx. 2-3-78</u>		

* Witness .1

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48 "</u>		<u>400</u>	<u>cin</u>
* <u>12 1/4"</u>	<u>8 7/8"</u>	<u>36 "</u>		<u>1500</u>	<u>cin</u>
<u>7 7/8"</u>	<u>5 1/2"</u>	<u>17-23</u>		<u>5700</u> <u>8700</u>	<u>-</u>

Casing Data:

Surface 35 joints of 8 7/8 inch 36 # Grade J-55
(Approved) (Rejected)

Inspected by M.S. date 1-30-78

Cementing Program

Size of hole 12 1/4 Size of Casing 8 7/8 Sacks cement required 900

Type of Shoe used pin Float collar used float Btm 3 jts welded yes

TD of hole 1415' Set 1514' Feet of 8 7/8 inch 36 # Grade J-55

New-used csg. @ 1514' with 200 sacks neat cement around shoe

+ 76.5 sax additives 5 gal. Alkyl - 4 gal. Plastic - 8 gal. water

Plug down @ 8:50 (AM) (PM) Date 2-3-78

Cement circulated yes No. of Sacks 55 =

Cemented by H. S. Johnson Witnessed by M. S. Johnson

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Run to 1080' 1 centralizer @ 1414'
1 centralizer 1434'