

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>C.E. Lohr & B.V. Muncy Jr.</u>		Lease <u>Kindle</u>		Well # <u>3</u>	
Location of Well	Unit <u>B</u> <u>2310C</u>	Section <u>26</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>Co. Tools.</u>		Type of Equipment <u>Pottery & start approx. 1-28-78</u>		
<u>* witness</u> <u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>9 7/8"</u>	<u>7"</u>	<u>23</u>		<u>920</u>	<u>275 circ.</u>
<u>6 1/4"</u>	<u>4 1/2"</u>	<u>10.5</u>		<u>1150</u>	<u>100 circ.</u>
Casing Data:					
Surface <u>28</u> joints of <u>7"</u> inch <u>23</u> # Grade <u>J-55</u>					
(Approved) (Rejected)					
Inspected by <u>M.S.</u> date <u>1-30-78</u>					
Cementing Program					
Size of hole <u>9 7/8</u> Size of Casing <u>7"</u> Sacks cement required <u>370</u> #					
Type of Shoe used <u>Flapper</u> Float ^{shoe} collar used <u> </u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>910'</u> Set <u>905'</u> Feet of <u>7"</u> Inch <u>23</u> # Grade <u>J-55</u>					
New-used csg. @ <u>905'</u> with <u>370</u> sacks neat cement around shoe					
+ <u> </u> sax <u> </u> additives <u> </u>					
Plug down @ <u>3:25</u> (AM) (PM) Date <u>1-30-78</u>					
Cement circulated <u>NO</u> No. of Sacks <u> </u>					
Cemented by <u>Dowell</u> Witnessed by <u>Mike Stillfield</u>					
Temp. Survey ran @ <u>7:30</u> (AM) (PM) Date <u>1-31-78</u> top cement @ <u>425'</u>					
Casing test @ <u> </u> (AM) (PM) Date <u> </u>					
Method Used <u> </u> Witnessed by <u> </u>					
Checked for shut off @ <u> </u> (AM) (PM) Date <u> </u>					
Method used <u> </u> Witnessed by <u> </u>					
Remarks: <u>Best dry break @ 800'</u>					

1st Run 2 1/2 jts 1" Tagged TOC @ 430'
1-31-78 7:00 pumped 100 sks 37% c.c.
2nd Tagged Top of cement @ 410'
2-2-78 1:00pm pumped 100 sks 47% c.c.
3rd Tagged TOC @ 75'
2-3-78 8:00am pumped 200 sks class c w/ 37% c.c.
4th Tagged TOC @ 70'
2-3-78 pumped 50 sks class H w/ 37% c.c. - 2nd run 1 sks T thru pit