

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Amoco Prod. Co.</i>		Lease <i>Griffin Com.</i>		Well # <i>1</i>	
Location of Well	Unit <i>1650N 1980W</i>	Section <i>4</i>	Township <i>18</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor	<i>Landis Drilling Co. Dig 4</i>		Type of Equipment <i>Rotary to start 2-24-78</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>13 7/8"</i>	<i>48</i>		<i>400</i>	<i>Cin</i>
<i>12 1/4"</i>	<i>8 5/8"</i>	<i>32</i>		<i>1250</i>	<i>"</i>
<i>7 7/8"</i>	<i>5 1/2"</i>	<i>15.5 + 17</i>		<i>8500</i>	

Casing Data:

Inter
Surface *29* joints of *8 5/8* inch *32* # Grade *J-55*

(Approved) (Rejected)

Inspected by *M.S.* date *3-3-78*

Cementing Program

Size of hole *12 1/4* Size of Casing *8 5/8* Sacks cement required *1050*

Type of Shoe used *pattern* Float collar used *yes* Btm 3 jts welded *yes*

TD of hole *1251'* Set *125'* Feet of *8 5/8* Inch *32* # Grade *J-55*

New-used csg. @ *1251'* with *2002* sacks neat cement around shoe

+ *300* sax *thick set* additives *10# gilsonite 1/4# Floeole*

Plug down @ *7:30* (AM) (PM) Date *3-3-78*

Cement circulated *yes* No. of Sacks *24*

Cemented by *Halliburton* Witnessed by *Mike Stubbins*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *+550 sks Hall. Lite 5# gilsonite 1/4# Floeole 8# salt*

** 3 centralizers @ 1211' @ 1171' @ 1131'*

Water @ 360'-700', 779'-836', 840'-1012', 1023'-34', 1040'-1063'