

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Gates Lbr Corp.</u>		Lease <u>Cities 56-State com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>P</u>	Section <u>12</u>	Township <u>18</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	<u>Monroe Rig 5</u>		Type of Equipment <u>Rotary</u>		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8"</u>	<u>48</u>		<u>300</u>	<u>300 cu.</u>
* <u>12 1/4</u>	<u>8 5/8"</u>	<u>24</u>		<u>1090</u>	<u>500 "</u>
<u>7 7/8"</u>	<u>5 1/2 or 4 1/2"</u>			<u>8600</u>	<u>250</u>

Casing Data:

Intermediate

~~Surface~~ joints of 8 5/8 inch 24 # Grade J-55

Mike Williams (Approved) (Rejected)

Inspected by _____ date 10-30-78

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required _____

Type of Shoe used Texas Pattern float collar used Insert Btm 3 jts welded yes

TD of hole 1050 Set 1058 Feet of 8 5/8 Inch 24 # Grade J-55

New ~~and~~ csg. @ 1058 with 150 sacks neat cement around shoe

+ 450 sax 50-50 Pos Mix additives

Plug down @ 10:00 (AM) (PM) Date 10-31-78

Cement circulated No No. of Sacks _____

Cemented by Dowell Witnessed by BW Weaver

Temp. Survey ran @ 330 (AM) (PM) Date 10-31-78 top cement @ 320

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Ran 1" Pipe to 320ft and circulated Cement with
125 SX of Class C Cement