

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Petr. Corp.</u>		Lease <u>State J.M. Corn.</u>		Well # <u>1</u>	
Location of Well	Unit <u>660 N 660 E</u>	Section <u>25</u>	Township <u>18</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	<u>Moranco</u>		Type of Equipment <u>Rotary to start approx 10-21-78</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 7/8"</u>	<u>48</u>		<u>300</u>	<u>200 cins.</u>
<u>12 1/4"</u>	<u>8 7/8"</u>	<u>24</u>		<u>1080</u>	<u>550 "</u>
<u>7 7/8"</u>	<u>5 1/2 or 4 1/2</u>			<u>8650</u>	<u>250</u>

Casing Data:

Surface _____ joints of 8 5/8 inch 24 # Grade J-55
Yes (Approved) (~~Rejected~~)

Inspected by B.W. Weaver date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required _____

Type of Shoe used Texas Float collar used Insert Btm 3 jts welded Yes

TD of hole 1070 Set 1076 Feet of 8 5/8 inch 24 # Grade J-55

New-~~used~~ csg. @ 8 5/8 with 150 sacks neat cement around shoe
+ 300 Thick Set sax 475 Hawco Lite additives

Plug down @ 1:00 (~~AM~~) (PM) Date 10-31-78

Cement circulated Yes No. of Sacks 300

Cemented by Hawco Witnessed by B.W. Weaver

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: 1" with 100 sap class C.