

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Rebr. Corp.</i>		Lease <i>O Neil J I</i>		Well # <i>1</i>	
Location of Well	Unit <i>23 10 N 16 50 E</i>	Section <i>33</i>	Township <i>18</i>	Range	County <i>26</i>
Drilling Contractor <i>La Rue + Mummy</i>		Type of Equipment <i>Rotary</i>			
<div style="display: flex; justify-content: space-between;"> <i>Jim Johnson company man</i> <u>APPROVED CASING PROGRAM</u> </div>					
<i>* witness</i>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>9 5/8"</i>	<i>7"</i>	<i>20</i>		<i>1120</i>	<i>550 cts.</i>
<i>6 1/4"</i>	<i>4 1/2 x 5 1/2"</i>			<i>3000</i>	<i>175 cts.</i>
Casing Data:					
Surface _____ joints of <i>7</i> inch <i>20</i> # Grade <i>J-55</i>					
(Approved) (Rejected)					
Inspected by <i>BW Weaver</i> date <i>12/3/78</i>					
Cementing Program					
Size of hole <i>9 1/2</i> Size of Casing <i>7"</i> Sacks cement required <i>400 sx</i>					
Type of Shoe used <i>guide</i> Float collar used <i>insert</i> Btm 3 jts welded <i>yes</i>					
TD of hole <i>1116'</i> Set <i>1116'</i> Feet of <i>7</i> Inch <i>20</i> # Grade <i>J-55</i>					
New-used csg. @ <i>1116'</i> with <i>150</i> sacks neat cement around shoe					
+ <i>250</i> sax <i>50-50</i> po. additives <i>4% D²⁰ (Bentonite), 10% colite, 1/4% caloflu, 3% occ</i>					
Plug down @ <i>4:30</i> (AM) (PM) Date <i>12/3/78</i>					
Cement circulated <i>yes</i> No. of Sacks <i>90 sx</i>					
Cemented by _____ Witnessed by _____					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: _____					
<i>brackets @ 916' + 616'</i>					
<i>centralizers @ 1075' - 916' - 616'</i>					
<i>Last ddy break @ 1014'</i>					