

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESTA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Mesa Petr. Co.</u>		Lease <u>Rio State</u>		Well # <u>1</u>	
Location of Well	Unit <u>1980s+u</u>	Section <u>36</u>	Township <u>18</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	<u>And Only Co.</u>		Type of Equipment <u>Rotary to start 3-5-79</u>		

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 7/8"</u>	<u>48</u>		<u>350</u>	<u>375 circ</u>
* <u>12 1/4"</u>	<u>8 7/8"</u>	<u>24</u>		<u>1200</u>	<u>600 "</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>10.5 + 11.6</u>		<u>9000</u>	<u>1025</u>

Casing Data:

Int 29 joints of 8 5/8 inch 24 # Grade K-55
~~Surface~~ ☒ (Approved) ☐ (Rejected)

Inspected by MW date 3/17/79

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 800

Type of Shoe used Guide Float collar used Insert Btm 3 jts welded Yes

TD of hole 1155 Set 1161 Feet of 8 5/8 Inch 24 # Grade K-55

New-used csg. @ 1155 with 200 sacks neat cement around shoe w/ 2% CC
 + 400 sax 65/35 Poz additives 5# Rolite 1/4" Flocle 2% CC + 200 SXRFC w/ 10# Rolite 1/4" Flocle 2% CC

Plug down @ 6:00 (AM) (PM) Date 3/17/79

Cement circulated Yes No. of Sacks 200

Cemented by Dowell Witnessed by MW

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Centralizers + Baskets e 371-578-784
Lost Circ or partially Lost Circ e 386' + 835'
Surface pipe set e 364' w/ 375 SX Class C - Circ