

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Hondo oil &amp; Gas Co.</i>		Lease <i>Beauregard Com.</i>		Well # <i>1</i>	
Location of Well	Unit <i>1980S</i> <i>1980W</i>	Section <i>23</i>	Township <i>18</i>	Range <i>27</i>	County <i>Eddy</i>
Drilling Contractor			Type of Equipment <i>Rotary to start approx. 3-15-79</i>		

APPROVED CASING PROGRAM

\* witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2</i>	<i>13 7/8"</i>	<i>54.5 K-55</i>		<i>400</i>	<i>600 Circ.</i>
<i>11</i>	<i>8 7/8"</i>	<i>32-5-80</i>		<i>2500</i>	<i>1325 "</i>
<i>7 7/8"</i>	<i>4 1/2"</i>	<i>11.6 MN80+K-55</i>		<i>10200</i>	<i>2600 "</i>

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch # Grade \_\_\_\_\_

(Approved) (Rejected) \_\_\_\_\_

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole *12 1/4* Size of Casing *8 5/8* Sacks cement required *1250 s x*

Type of Shoe used *Float* Float collar used *yes* Btm 3 jts welded *yes*

TD of hole *2500'* Set *2500'* Feet of *8 5/8* Inch *28* # Grade *S-80*

New-used csg. @ *2500'* with *200 2 1/2* sacks neat cement around shoe

+ *1050* sax *Hall. Oite* additives *1/4# floeade- 5# gilsomite 8# salt*

Plug down @ *9:45* (AM) (PM) Date *3/28/79*

Cement circulated *yes* No. of Sacks *350 s x*

Cemented by *Halliburton* Witnessed by *Mike Stubblefield*

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: \_\_\_\_\_

*Centrifuges @ 2490-2450-2410-2380*