

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 9D
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Mesa Petr. Co.</i>		Lease <i>Rio State</i>		Well # <i>2</i>	
Location of Well	Unit <i>19805+e</i>	Section <i>36</i>	Township <i>18</i>	Range <i>24</i>	County <i>Edm</i>
Drilling Contractor	<i>Art. Dwy Co. #4</i>		Type of Equipment <i>Pottery to start approx 6.5.79</i>		

* *witness*

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2</i>	<i>13 3/8</i>	<i>48</i>		<i>350</i>	<i>375 lin.</i>
* <i>12 1/4</i>	<i>8 5/8</i>	<i>24</i>		<i>1200</i>	<i>600 "</i>
<i>7 1/8</i>	<i>4 1/2</i>	<i>10.5 + 11.6</i>		<i>9000</i>	<i>1025</i>

Casing Data:

Surface *30* joints of *8 5/8* inch *24* # Grade *K-55*

(Approved) (Rejected)

Inspected by *M.S.* date *6/11/79*

Cementing Program

Size of hole *12 1/4* Size of Casing *8 5/8* Sacks cement required

Type of Shoe used *guide* Float collar used *yes* Btm 3 jts welded *yes*

TD of hole *1205'* Set *1205'* Feet of *8 5/8* Inch *24* # Grade *K-55*

New-used csg. @ *1205'* with *200* sacks neat cement around shoe

+ *400* sax *Hall-Lite* additives *5# gilsonite - 1/4# fluoride*

Plug down @ *3:10* (AM) (PM) Date *6/12/79*

Cement circulated *yes* No. of Sacks *50*

Cemented by *Halliburton* Witnessed by *Mike Stubbfield*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks:

centralizers @ 1185'-1100'-1023'

last July Break @ 906'