

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Pet. Corp.</i>		Lease <i>Bryan ME</i>		Well # <i>1</i>	
Location of Well	Unit <i>1650 N 2310 W</i>	Section <i>33</i>	Township <i>18</i>	Range <i>26</i>	County <i>El Paso</i>
Drilling Contractor	<i>Cactus Drilling Co. #52</i>		Type of Equipment		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>9 1/2"</i>	<i>7"</i>	<i>20</i>		<i>1120</i>	<i>400 lbs.</i>
<i>6 1/4"</i>	<i>4 1/2"</i>			<i>3000</i>	<i>275 lbs.</i>

Casing Data:

Surface \_\_\_\_\_ joints of *7* inch *20* # Grade *J-55*  
(Approved) (Rejected)

Inspected by *M.S.* date *1/25/80*

Cementing Program

Size of hole *9 1/2"* Size of Casing *7"* Sacks cement required \_\_\_\_\_

Type of Shoe used *guide* Float collar used *inert* Btm 3 jts welded *yes*

TD of hole *1108'* Set *1108'* Feet of *7"* Inch *20* # Grade *J-55*

New-used csg. @ *1108'* with *150 27cc* sacks neat cement around shoe

+ *200* sac *50/50* port. additives *5# Kolite - 1/4# celoflakes - 2# gel - 290cc*

Plug down @ *7:30* (AM) (PM) Date *1/26/80*

Cement circulated *yes* No. of Sacks *35* sk

Cemented by *Dowdell* Witnessed by *Mike Stillfield*

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks:

*No centralizers*

*last drill break @ 998'*