

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gabe Petr. Corp</i>		Lease <i>Eddie NE</i>		Well # <i>1</i>	
Location of Well	Unit <i>990N 2310W</i>	Section <i>33</i>	Township <i>18</i>	Range <i>26</i>	County <i>Eddy</i>
Drilling Contractor	<i>Cactus Drilling Co.</i>		approved <i>2-8-80</i> Type of Equipment <i>Rotary to start soon as approved</i>		

APPROVED CASING PROGRAM

* witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>9 1/2"</i>	<i>7"</i>	<i>20</i>		<i>1120</i>	<i>550 275 ccs</i>
<i>6 1/4"</i>	<i>4 1/2"</i>	<i>9.5</i>		<i>3100</i>	<i>275 "</i>

Casing Data:

Surface _____ joints of *7"* inch *20* # Grade *K-55*
(Approved) (Rejected) _____

Inspected by *M.S.* date *2/15/80*

Cementing Program

Size of hole *9 1/2"* Size of Casing *7"* Sacks cement required _____

Type of Shoe used *guide* Float collar used *insert* Btm 3 jts welded *yes*

TD of hole *1080'* Set *1076'* Feet of *2* Inch *20* # Grade *K-55*

New-used csg. @ *1076'* with *150 270cc* sacks neat cement around shoe

+ *225* sac *50/50* per. additives (*1/4# celuflex, 5# Kolite, 270cc, 270gel*)

Plug down @ *11:45* (AM) (PM) Date *2/16/80*

Cement circulated *yes* No. of Sacks *30*

Cemented by *Dowell* Witnessed by *Mike Stillfield*

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____

Full returns to 1080'

No centralizers

last day back to 979'