

OIL CONSERVATION DIVISION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

|                                 |                 |                  |                                 |                 |                    |
|---------------------------------|-----------------|------------------|---------------------------------|-----------------|--------------------|
| Operator <u>Yates Petr Corp</u> |                 |                  | Lease <u>Stromberg CR</u>       |                 | Well # <u>1</u>    |
| Location of Well                | Unit <u>10</u>  | Section <u>1</u> | Township <u>18</u>              | Range <u>26</u> | County <u>Lddy</u> |
| Drilling Contractor             | <u>L + R #1</u> |                  | Type of Equipment <u>Rotary</u> |                 |                    |

\*Unknown  
APPROVED CASING PROGRAM

| Size of Hole         | Size of Casing       | Weight Per Foot      | New or Used | Depth       | Sacks Cement         |
|----------------------|----------------------|----------------------|-------------|-------------|----------------------|
| <u>17 1/2 15</u>     | <u>15 1/2 10 3/4</u> | <u>22 3#</u>         |             | <u>360</u>  | <u>500 5X Class</u>  |
| <u>12 1/4 11 1/2</u> | <u>7</u>             | <u>20#</u>           |             | <u>1300</u> | <u>1500 5X Class</u> |
| <u>7 7/8 6 1/4</u>   | <u>4 1/2</u>         | <u>16 1/2 11 1/2</u> |             | <u>TD</u>   | <u>2000 5X</u>       |

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected)

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 9 1/2 Size of Casing 7 Sacks cement required \_\_\_\_\_

Type of Shoe used Texas Petro Float collar used Insert Btm 3 jts welded yes

TD of hole 1041 Set 1049 Feet of 7 Inch 20 # Grade \_\_\_\_\_

New-~~used~~ csg. @ 1049 with 150 sacks neat cement around shoe

+ 400 sax Lite Pos additives 8" Gilsomite 1/4 Flo-fal 3% Calcium Chloride

Plug down @ 4:30 (AM) (PM) Date 11-12-80

Cement circulated NO No. of Sacks \_\_\_\_\_

Cemented by Dewell Witnessed by Bow Weaver

Temp. Survey ran @ 9:30 (AM) (PM) Date 11-12-80 top cement @ 380

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: Last Drilling Break @ 928 Loss Circulation @ 876 Full

Returns @ TD 1041

Ran 1" to 380ft and Cemented with 84 5X Class 2% Calcium Chloride  
Cement Did Circulate.