

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Petroleum Corp</u>		Lease <u>Anderson State CS</u>		Well # <u>2</u>	
Location of Well	Unit <u>1L505 1980E J</u>	Section <u>14</u>	Township <u>18</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor <u>Landis Rig #4</u>		Type of Equipment <u>Rotary ASAP</u>			
* Witness _____					
<u>APPROVED CASING PROGRAM</u>					
Size of Hole <u>12 1/4"</u>	Size of Casing <u>8 5/8"</u>	Weight Per Foot <u>24 #</u>	New or Used	Depth <u>1000'</u>	Sacks Cement <u>550 SX - Circ</u>
<u>7 7/8"</u>	<u>5 1/2 or 4 1/2</u>	<u>10.5 17# R-SS</u> <u>10.5 11.6# R-SS</u>		<u>8750</u>	<u>300 SX</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required _____					
Type of Shoe used <u>Tex-Pat</u> Float collar used <u>Insert</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>1043</u> Set <u>1046</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J-55</u>					
New-used csg. @ <u>1046</u> with <u>150</u> sacks neat cement around shoe					
+ <u>300</u> sax <u>Hawco lite</u> additives _____					
Plug down @ <u>6.00</u> (AM) (PM) Date <u>11-22-81</u>					
Cement circulated <u>yes</u> No. of Sacks <u>50</u>					
Cemented by <u>Hawco</u> Witnessed by <u>B.W. Weaver</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>NO LOSS ZONE</u>					