

NEW MEXICO OIL CONSERVATION COMMISSION  
DEALER ID  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Reade &amp; Stevens Inc.</u>		Lease <u>Fair</u>		Well # <u>1</u>	
Location of Well	Unit <u>1980 N</u> <u>1985 W F</u>	Section <u>30</u>	Township <u>18</u>	Range <u>27</u>	County <u>Eddy</u>
Drilling Contractor <u>Sierra Dr. &amp; Co.</u>			Type of Equipment <u>Rotary</u> <u>2-15-82</u>		
* WITNESS					
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17.5"</u>	<u>13.375</u>	<u>54.5 #</u>		<u>360'</u>	<u>400 Sx. circ</u>
<u>12.25"</u>	<u>8.625</u>	<u>24.0 #</u>		<u>2000</u>	<u>1000 Sx. circ</u>
<u>7.88"</u>	<u>5.5</u>	<u>17.0 #</u>		<u>10,000</u>	<u>900 Sx.</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected)					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required <u>1000 Sx.</u>					
Type of Shoe used <u>NECH</u> Float collar used <u>FICAT</u> <u>SIZE</u> Bit 3 jts welded <u>yes</u>					
TD of hole <u>1808</u> Set <u>1804</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>K-55</u>					
New used csg. @ <u>1808</u> with <u>200</u> sacks neat cement around shoe C.I.C 29% Cell					
+ <u>800</u> sax <u>Hall. lite</u> additives <u>5# Gilsomite</u> , <u>1/4# Flocele.</u>					
Plug down @ <u>10:30</u> <u>AM</u> (PM) Date <u>3/21/82</u>					
Cement circulated <u>YES</u> No. of Sacks <u>50 to the pit</u>					
Cemented by <u>Halliburton</u> Witnessed by <u>Larry Brooks</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: _____					