

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Ralph Nix</u>		Lease <u>Kelly</u>		Well # <u>2</u>	
Location of Well	Unit <u>16505 2310W</u> <u>K</u>	Section <u>27</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>Salazar Bros</u>		Type of Equipment <u>Rotary</u> <u>ASAP</u>		

\* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>9 1/2</u>	<u>7"</u>	<u>20<sup>#</sup></u>		<u>1120</u>	<u>525-Circ</u>
<u>6 1/4</u>	<u>4 1/2"</u>	<u>10.5<sup>#</sup></u>		<u>3600</u>	<u>375-Circ</u>

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected)

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 9 7/8" Size of Casing 7" Sacks cement required \_\_\_\_\_

Type of Shoe used guide Float collar used insert Btm 3 jts welded yes

TD of hole 1120' Set 1120' Feet of 7" Inch 20 # Grade J-55

New-used csg. @ 1120' with 50 2%cc sacks neat cement around shoe  
+ 300 sax Hall. Date additives (6# gel., 1/4# floreal, 3%cc)

Plug down @ 4830 (AM) (PM) Date 4/29/82

Cement circulated Yes No. of Sacks 90 sax

Cemented by Halliburton

Witnessed by Mike Shultzfield

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: \_\_\_\_\_

No centralizers

lost dily break @ 970'