

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Ralph Nix</u>		Lease <u>Merrill Batt. #2</u>		Well # <u>3</u>	
Location of Well	Unit <u>G</u>	Section <u>34</u>	Township <u>18 S</u>	Range <u>26 E</u>	County <u>Eddy</u>
Drilling Contractor	<u>Salazar Bros.</u>		Type of Equipment <u>Rotary</u>		
<u>APPROVED CASING PROGRAM</u>					
* WITNESS					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* <u>12 1/4</u>	<u>8 5/8</u>	<u>24<sup>lb</sup></u>	<u>NEW</u>	<u>910</u>	<u>CIRC</u>
<u>7 7/8</u>	<u>5 1/2"</u>	<u>15.5<sup>lb</sup></u>	<u>NEW</u>	<u>3900</u>	<u>CIRC</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____ (Approved) (Rejected)					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required _____					
Type of Shoe used <u>Tex-Rt</u> Float collar used <u>Insert</u> Btm 3 jts welded <u>Yes</u>					
TD of hole <u>935</u> Set <u>937</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J-55</u>					
New-used csg. @ <u>937</u> with <u>200</u> sacks neat cement around shoe					
+ <u>300</u> sax <u>Henco 1/2c</u> additives <u>#6 Gilsomite 1/4 Flo Seal 3% C C</u>					
Plug down @ <u>6:00</u> (AM) (PM) Date <u>2-17-83</u>					
Cement circulated <u>Yes</u> No. of Sacks <u>35 5X</u>					
Cemented by <u>Henco</u> Witnessed by <u>BW Weaver</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Loss Circulation @ 804 Last Drily Break 817 ft</u>					