

## ARTESIA, NEW MEXICO

## FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Co</u>		Lease <u>Krauss GE</u>		Well # <u>2</u>	
Location of Well	Unit <u>L</u>	Section <u>22</u>	Township <u>18</u>	Range <u>26</u>	County <u>EDDY</u>
Drilling Contractor <u>LARUE # 2</u>			Type of Equipment <u>ROTARY</u>		
<p><b>* Witness</b> <span style="float:right"><u>APPROVED CASING PROGRAM</u></span></p>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 1/2"</u>	<u>10 3/4"</u>	<u>32 #</u>	<u>NEW</u>	<u>350</u>	<u>CIRC</u>
<u>9 1/2"</u>	<u>7"</u>	<u>30 #</u>	<u>NEW</u>	<u>1150</u>	<u>CIRC</u>
<u>6 1/4"</u>	<u>4 1/2"</u>	<u>10.5 #</u>	<u>NEW</u>	<u>TD</u>	<u>150 Sx</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>9 7/8"</u> Size of Casing <u>7</u> Sacks cement required <u>550</u>					
Type of Shoe used <u>TEX. PT NOTCHED</u> Float collar used <u>INST. FLAPPER</u> Btm 3 jts welded <u>YES</u>					
TD of hole <u>1137</u> Set <u>1164</u> Feet of <u>7</u> Inch <u>23</u> # Grade <u>J-55</u>					
New-used csg. @ <u>1137</u> with <u>150</u> sacks neat cement around shoe C.I.C 4% CaCl <sub>2</sub>					
+ <u>400</u> sax <u>PACESETTER LITE</u> additives <u>1/4# celocal + 3% CaCl<sub>2</sub></u>					
Plug down @ <u>10:00</u> <u>(AM)</u> (PM) Date <u>7/24/83</u>					
Cement circulated <u>YES</u> No. of Sacks <u>50 SXS.</u>					
Cemented by <u>WESTERN</u> Witnessed by <u>Larry Brooks</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: _____					