

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Exp. 1-26-85

Operator <u>YATES PET. CORP</u>		Lease <u>WRIGHT J</u> <u>7A</u>		Well # <u>5</u>	
Location of Well	Unit <u>F</u>	Section <u>34</u>	Township <u>18S</u>	Range <u>26E</u>	County <u>EDDY</u>
Drilling Contractor	<u>LARUE</u>		Type of Equipment <u>ROTARY</u>		
<p>* = CSG. TO WITNESS</p> <p style="text-align: center;"><u>APPROVED CASING PROGRAM</u></p>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
* <u>12 1/4"</u>	<u>8 5/8"</u>	<u>24 #</u>	<u>NEW</u>	<u>950</u>	<u>CIRC</u>
<u>7 7/8"</u>	<u>4 1/2 or 5 1/2</u>	<u>9.5# or 14#</u>	<u>"</u>	<u>TD</u>	<u>500 SXS or circ</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4"</u> Size of Casing <u>8 5/8"</u> Sacks cement required _____					
Type of Shoe used <u>guide</u> Float collar used <u>insert</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>920'</u> Set <u>920'</u> Feet of <u>8 5/8"</u> Inch <u>24</u> # Grade <u>J-55</u>					
New/used csg. @ <u>920'</u> with <u>150 2%cc</u> sacks neat cement around shoe					
+ <u>310</u> sax <u>Pacesetter lite</u> additives (<u>1/4# celvex</u> , <u>10# gilsrite</u> , <u>3%cc</u>)					
Plug down @ <u>3300</u> (AM) (PM) Date <u>9/9/84</u>					
Cement circulated <u>No</u> No. of Sacks <u>- 0 -</u>					
Cemented by <u>Western Co.</u> Witnessed by <u>M.S.</u>					
Temp. Survey ran @ <u>9:00</u> (AM) (PM) Date <u>9/9/84</u> top cement @ <u>400'</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: _____					
<p><u>last dily break @ 816'</u></p> <p><u>last returns 280-300. 50% returns @ TD</u></p>					

1. Ran 1" + tagged to c @ 366'
cmt w/ 75 sx C 3%cc
2. Ran 1" + tagged to c @ 315'
cmt w/ 35 sx C 3%cc.
3. Ran 1" + tagged to c @ 200'
cmt w/ 135 sx C 3%cc
cmt circulated to surface.