

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Exp 3 26-85

Operator <u>YPC</u>		Lease <u>COLE</u>		AAE <u>COM</u>		Well # <u>1</u>
Location of Well	Unit <u>J</u>	Section <u>5</u>	Township <u>18 S</u>	Range <u>26 E</u>	County <u>Eddy</u>	
Drilling Contractor	<u>N/A</u>		Type of Equipment <u>ROTARY</u>			

\* = CSG. TO WITNESS

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
17 1/2"	13 3/8"	48 #	New	500	CIRC
* 12 1/4"	8 5/8"	24 #	New	1360	CIRC
7 7/8"	5 1/2" or 4 1/2"	15.5 or 17 # 10.5-11.6	New	TD	250

Casing Data:

Surface 24 joints of 8 5/8 inch 24 # Grade K-55  
yes (Approved) (Rejected)

Inspected by BW Weaver date \_\_\_\_\_

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 200

Type of Shoe used Tex-Rat Float collar used Insert Btm 3 jts welded yes

TD of hole 1363 Set 1363 Feet of 8 5/8 Inch 24 # Grade K-55

New-used csg. @ 1363 with 200 sacks neat cement around shoe

+ 180 sax Pace Setter l/c additives 3% cc

Plug down @ 930 (AM) (PM) Date 10-22-84

Cement circulated No No. of Sacks \_\_\_\_\_

Cemented by Western Witnessed by BW Weaver

Temp. Survey ran @ 500 (AM) (PM) Date 10-23-84 top cement @ 620

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: Tag Cement 517 FT Cemented with 3155X Class C 2% CC

Circulated Cement