

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

4-11-85

|                                     |                  |                          |                                    |                     |                       |
|-------------------------------------|------------------|--------------------------|------------------------------------|---------------------|-----------------------|
| Operator<br><b>Blanco Eng. Inc.</b> |                  | Lease<br><b>Williams</b> |                                    | Well #<br><b>9</b>  |                       |
| Location of Well                    | Unit<br><b>G</b> | Section<br><b>25</b>     | Township<br><b>18S</b>             | Range<br><b>26E</b> | County<br><b>Eddy</b> |
| Drilling Contractor                 | <b>L&amp;M</b>   |                          | Type of Equipment<br><b>ROTARY</b> |                     |                       |

\* = CSG. TO WITNESS

APPROVED CASING PROGRAM

| Size of Hole | Size of Casing | Weight Per Foot | New or Used | Depth | Sacks Cemen |
|--------------|----------------|-----------------|-------------|-------|-------------|
| * 12 1/4     | 8 5/8"         | 24 #            | NEW         | 930'  | CIRC        |
| 7 7/8        | 5 1/2"         | 15.5 #          | "           | 3750' | CIRC        |
|              |                |                 |             |       |             |

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected) \_\_\_\_\_

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 12 1/4" Size of Casing 8 5/8" Sacks cement required \_\_\_\_\_

Type of Shoe used guide Float collar used insert Btm 3 jts welded yes

TD of hole 965' Set 965' Feet of 8 5/8" Inch 24 # Grade J-55

New-used csg. @ 965' with 200 2%cc sacks neat cement around shoe

+ 300 sax CL. C additives (10# colored, 29cc)

Plug down @ 5:30 (AM) (PM) Date 11/3/84

Cement circulated yes No. of Sacks 505x

Cemented by Denton cementing Witnessed by M.S.

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: \_\_\_\_\_