

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Exp. 5-20-85

Operator <u>YPC</u>		Lease <u>GATES AAC</u>		Well # <u>2</u>	
Location of Well	Unit <u>D</u>	Section <u>22</u>	Township <u>18</u>	Range <u>26</u>	County <u>EDDY</u>
Drilling Contractor	<u>AFT #2</u>		Type of Equipment <u>ROTARY</u>		

* = CSG. TO WITNESS

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
* 12 1/4 "	8 5/8"	24#	NEW	950	CIRC
7 7/8"	5 1/2"	14#	"	TD	CIRC

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required _____

Type of Shoe used guide Float collar used insert Btm 3 jts welded yes

TD of hole 914 Set 926 Feet of 8 5/8 Inch 24# # Grade J-55

New-used csg. @ 914 with 150 sacks neat cement around shoe 2% CaCl₂

+ 325 sax PaceSetter lite additives 10# Hiseal, 1/4# Cellogel, 3% CaCl₂

Plug down @ 6:15 (AM) (PM) Date 11-31-84

Cement circulated NO No. of Sacks _____

Cemented by WESTERN Witnessed by Ramy Brooke

Temp. Survey ran @ 12:15 (AM) (PM) Date 11-31-84 top cement @ 310

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Tagged @ 310' pumped 60 sxs. Cmt. tagged @ 119' pumped

75 sxs. cmt. circ. 10 sxs. to the D.T. * Cl.C 3% CaCl₂