

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>H + S Oil Co.</u>		Lease <u>INEX</u>		Well # <u>2</u>	
Location of Well	Unit <u>G</u>	Section <u>26</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>Artesia Fishing Tool</u>		Type of Equipment <u>Rotary</u>		

* Witness

APPROVED CASING PROGRAM

Exp. 5-13-86

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>12 1/2</u>	* <u>8 5/8</u>	<u>24 #</u>		<u>960*</u>	<u>700 Circ</u>
<u>7 7/8</u>	<u>5 1/2</u>	<u>15 #</u>		<u>3670</u>	<u>670</u>

Casing Data:

* Or 100' Below last break.

Surface _____ joints of _____ inch _____ # Grade _____

(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/2 Size of Casing 8 5/8 Sacks cement required 600 sacksType of Shoe used Guide Float collar used Insert float Btm # jto welded _____TD of hole 936 Set 926 Feet of 8 5/8 Inch 24 # Grade _____New/used csg. @ 926 with 400 sacks neat cement around shoe+ 200 sack _____ additives 2% calcium chloride, 1/4 sack of cellophane flakesPlug down @ 11:00 (AM) (PM) Date 12/7/85Cement circulated No No. of Sacks _____

Cemented by _____ Witnessed by _____

Temp. Survey ran @ 5:30 (AM) (PM) Date 12/7/85 top cement @ 47'

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks:

400 sacks LW II 2% Calcium chloride, 1/4 sack cellophane flakes200 sacks HE II 2% Calcium chlorideLast Drtg Break 830Last some fluid at 100'