

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Yates Petr Corp</u>		Lease <u>Northwestern Shores ADL Com</u>		Well # <u>1</u>	
Location of Well	Unit <u>0</u>	Section <u>25</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		
660/5 1980/E					
* Witness APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8</u>	<u>54.5 # J-55</u>		<u>550</u>	<u>500 Circ</u>
<u>12 1/4</u>	* <u>8 5/8</u>	<u>24 # J-55</u>		<u>1300</u>	<u>1500 Circ</u>
<u>7 7/8</u>	<u>5 1/2</u>	<u>17 # K-55</u>		<u>TD</u>	
Casing Data: <u>+ N-80</u>					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required <u>500</u>					
Type of Shoe used <u>Guide</u> Float collar used <u>Insert</u> Btm 3 jts welded <u>Yes</u>					
TD of hole <u>1305</u> Set <u>1305</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J-55</u>					
New-used csg. @ <u>1305</u> with <u>300</u> sacks neat cement around shoe					
+ <u>200</u> sax <u>Class C</u> additives <u>2% CaCl</u> <u>1/4 lb sack cellophane</u>					
Plug down @ <u>9:00</u> (AM) (PM) Date <u>1/27/86</u>					
Cement circulated <u>No</u> No. of Sacks _____					
Cemented by <u>Western</u> Witnessed by <u>Darrell Moore</u>					
Temp. Survey ran @ <u>4:00</u> (AM) (PM) Date <u>1/28/86</u> top cement @ <u>472 ft.</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used <u>(1") One inch</u> Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Ran 1" in hole and circulated cement.</u>					
<u>300 sacks Pacemaker 1/4 lbs sack cellophane 2% CaCl</u>					
<u>200 sacks Class C 2% CaCl</u>					

No lost Circ.
Last Drlg break 1176