

## FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Gates Petr. Corp.</u>		Lease <u>White IU</u>		Well # <u>3</u>	
Location of Well	Unit <u>I</u>	Section <u>28</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>2310/S 990/E</u> <u>LaRue Drilling Co.</u>		Type of Equipment <u>Rotary</u>		
* Witness <u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>12 1/4</u>	<u>* 8 5/8</u>	<u>24# K-55</u>		<u>960</u>	<u>600 Circ</u>
<u>7 7/8</u>	<u>5 1/2</u>	<u>15.5 K-55</u>		<u>3700</u>	<u>675 Circ</u>
Casing Data:					
Surface <u>          </u> joints of <u>8 5/8"</u> inch <u>24</u> # Grade <u>K-55</u> (Approved) (Rejected) <u>          </u>					
Inspected by <u>M.S.</u> date <u>12/4/86</u>					
Cementing Program					
Size of hole <u>12 1/4"</u> Size of Casing <u>8 5/8"</u> Sacks cement required <u>          </u>					
Type of Shoe used <u>guide</u> Float collar used <u>inert</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>970'</u> Set <u>970'</u> Feet of <u>8 5/8"</u> inch <u>24</u> # Grade <u>K-55</u>					
<del>New</del> -used csg. @ <u>970'</u> with <u>200 2%</u> sacks neat cement around shoe					
+ <u>500</u> sack <u>proccerite lite</u> additives <u>(1/4" colormed, 270cc)</u>					
Plug down @ <u>9:30</u> (AM) (PM) Date <u>12/5/86</u>					
Cement circulated <u>yes</u> No. of Sacks <u>73 sk</u>					
Cemented by <u>Western Company</u> Witnessed by <u>Michael Stillfield</u>					
Temp. Survey ran @ <u>          </u> (AM) (PM) Date <u>          </u> top cement @ <u>          </u>					
Casing test @ <u>          </u> (AM) (PM) Date <u>          </u>					
Method Used <u>          </u> Witnessed by <u>          </u>					
Checked for shut off @ <u>          </u> (AM) (PM) Date <u>          </u>					
Method used <u>          </u> Witnessed by <u>          </u>					
Remarks: <u>          </u>					
Full returns to TD					
Last drill break @ 861'					