

PAGE START DATE: 6/ 4/94
PAGE START TIME: 4:42: 0
DATA FILE: 2

DELTA TIME HRS	DEPTH FEET	TEMPERATURE 'F	COMMENTS
0.000	500.00	86.50	
0.417	1490.00	89.00	BREAK
0.425	1510.00	117.00	
0.433	1535.00	112.50	
0.467	1630.00	157.00	
0.483	1673.00	113.50	
0.500	1714.00	117.50	
0.508	1733.00	112.75	
0.533	1803.00	122.50	
0.542	1832.00	111.50	
0.550	1862.00	112.00	
0.558	1889.00	109.00	
0.567	1916.00	111.25	
0.575	1943.00	110.75	
0.583	1970.00	125.25	
0.592	1993.00	116.00	
0.600	2016.00	122.75	
0.617	2056.00	113.00	
0.650	2167.00	110.00	
0.667	2211.00	113.00	
0.700	2309.00	109.25	
0.717	2361.00	109.75	
0.733	2417.00	109.25	
0.750	2465.00	111.25	
0.767	2524.00	110.75	
0.783	2581.00	112.00	
0.817	2702.00	110.50	
0.833	2764.00	112.00	
0.850	2832.00	111.50	
0.867	2890.00	113.50	
0.900	3012.00	112.00	
0.933	3136.00	115.25	
0.950	3189.00	114.50	
0.983	3310.00	116.50	
1.000	3370.00	114.75	
1.017	3440.00	115.00	
1.050	3519.00	112.50	
1.067	3649.00	117.75	
1.100	3790.00	115.50	
1.117	3848.00	120.25	M.D.R.

DATE AND TIME CEMENT JOB COMPLETE:

JUNE 3, 1994 @ 10:00 P.M.

DATE AND TIME SURVEY MADE:

JUNE 4, 1994 @ 4:30 A.M.

AMOUNT AND TYPE OF CEMENT USED:

2500 SACKS 35/65 CLASS C POSMIX WITH
2% GEL, 12# SALT PER SACK, 2% CALCIUM
CHLORIDE AND ¼# FLOW SEAL PER SACK,
RUN BEHIND 4482 FEET OF 8-5/8" CASING
IN A 12½" HOLE.

DEPTH MEASURED FROM:

KELLY BUSHING