

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Lutes P & Corp</u>		Lease <u>Boyd BN</u>		Well # <u>1 H</u>	
Location of Well	Unit	Section	Township	Range	County
		<u>15</u>	<u>19</u>	<u>25</u>	<u>Eddy</u>
Drilling Contractor	<u>1980 N 660 E</u> <u>Lenthwood</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>12 1/4</u>	<u>9 5/8</u>	<u>36</u>	<u>New</u>	<u>1200</u>	<u>Circ</u>
<u>8 3/4</u>	<u>7-5/16</u>			<u>960</u>	<u>500</u>

Casing Data:

Surface _____ joints of 9 7/8 inch H&J 32.3 # Grade _____
(Approved) (Rejected)

Inspected by L. Hamitz date 7-19-68

Cementing Program

Size of hole 12 1/4 Size of Casing 9 5/8 Sacks cement required 542 Cu ft

Type of Shoe used Texas ^{Teeth} Float collar used ✓ Btm 3 jts welded Thread lock

TD of hole 1200 Set _____ Feet of 9 7/8 inch 32.3 # Grade 18 H

New-~~used~~ csg. @ TD with 100 sacks neat cement around shoe class C 2% Cu 1/2
+ 450 sax class C additives 4 1/2 gal 1 12 1/2 gal 1 1/4 flocc

Plug down @ 8:12 (AM) (PM) Date 7-26-68

Cement circulated ✓ No. of Sacks 100 more or less

Cemented by Hall, Burton Witnessed by L. Hamitz

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: 1