

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 110
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Mark Production Co.</i>		Lease <i>New Mexico Lease</i>		Well # <i>1</i>	
Location of Well	Unit <i>6603 1980e</i>	Section <i>5</i>	Township <i>20</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor	<i>Cactus & Co.</i>		Type of Equipment <i>Rotary to start 5-14-74</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>12 3/4"</i>	<i>32</i>		<i>300</i>	<i>350 ctn</i>
<i>11</i>	<i>8 7/8"</i>	<i>32</i>		<i>1250</i>	<i>375 ctn</i>
<i>7 7/8"</i>	<i>4 1/2"</i>	<i>10.5 & 11.6</i>		<i>10000</i>	<i>375</i>

Casing Data:

Surface _____ joints of *8 7/8"* inch *24436 #* Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole *11* Size of Casing *8 7/8"* Sacks cement required _____

Type of Shoe used *Guide* Float collar used *Insert* Btm 3 jts welded *Thread Lok*

ID of hole *1250* Set _____ Feet of *8 7/8"* inch *24436 #* Grade *J-*

New ~~used~~ csg. @ *1250* with *150* sacks neat cement around shoe *2700e*
+ *250* sax *HL* additives *5% Silica 1% Floc 2700e*

Plug down @ *4:20* (AM) (PM) Date *5-20-74*

Cement circulated *yes* No. of Sacks *38*

Cemented by _____ Witnessed by _____

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: *12 3/4" - 300 - 500 SX - 5 stages (3 Centralizer)*
Water - 938-1000