

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Read + Stevens Inc.</u>		Lease <u>Mesa Com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>1980NW</u>	Section <u>20</u>	Township <u>20</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor			Type of Equipment <u>Rotary to start 6-14-74</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 7/8"</u>	<u>48</u>		<u>200</u>	<u>300 Cmc.</u>
<u>12 1/4"</u>	<u>8 7/8"</u>	<u>24 + 36</u>		<u>3250</u>	<u>1200 cmc.</u>
<u>7 3/4"</u>	<u>5 1/2"</u>	<u>17 + 20</u>		<u>9800</u>	<u>400</u>

Casing Data:

Surface 89 joints of 2 7/8" inch # Grad 9023-32# 2235-#24
New and Used API (Approved) (Rejected)
 Inspected by S. A. Mearns date 6-24-74

Cementing Program

Size of hole 12 1/4" 2650' Size of Casing 8 7/8" 11" 6 3250' Sacks cement required 1200
 Type of Shoe used Lucy Float collar used Insert Btm 2 jts welded Yes
 TD of hole 3250KB Set 3234' Feet of 8 7/8" inch # Grade
 New-used csg. @ 3234' with 200 sacks neat cement around shoe class 14.8
 + 1000 sax Flowcelite additives 5# Silicate 4# Floccul. 12.8-13.0
 Plug down @ 11:50 (AM) (PM) Date 6-24-74
 Cement circulated Yes No. of Sacks 150/54
 Cemented by G. A. Mearns Witnessed by S. A. Mearns
 Temp. Survey ran @ (AM) (PM) Date top cement @
 Casing test @ (AM) (PM) Date
 Method Used Witnessed by
 Checked for shut off @ (AM) (PM) Date
 Method used Witnessed by
 Remarks: Sand zone 800' and '054' Did not base case completely.