

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Roger C Hanks</u>		Lease <u>Julie Com</u>		Well # <u>1</u>	
Location of Well	Unit <u>H</u>	Section <u>17</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor <u>1980 FNL 990 FEL</u>			Type of Equipment <u>Rotary Moran Bros</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8"</u>	<u>32"</u>		<u>410'</u>	<u>Circ</u>
<u>11</u>	<u>8 5/8"</u>	<u>24"</u>		<u>1100'</u>	<u>Circ</u>
<u>7 7/8</u>	<u>5 1/2"</u>	<u>20"</u>		<u>7950</u>	

Casing Data:

★ Surface 13 joints of 13 3/8 inch 54 # Grade J-55
(Approved) (Rejected)

Inspected by Nick Tinker date 7-20-76

Cementing Program

Size of hole 17 1/2 Size of Casing 13 3/8 Sacks cement required 300 SKs

Type of Shoe used Reg Float collar used None Btm 3 jts welded yes

TD of hole 3415 ~~Set~~ 4100' GL Feet of 13 3/8 inch 54 # Grade J-55

~~Used~~ csg. @ 34.5 with 200 sacks neat cement around shoe

+ sax additives 2% CaCl

Plug down @ 8:30 (AM) (PM) Date 7-20-76

Cement circulated yes No. of Sacks 80 SKs

Cemented by Holburner Witnessed by Nick Tinker Ken Fullum

Temp. Survey ran @ — (AM) (PM) Date — top cement @ Surface

Casing test @ — (AM) (PM) Date —

Method Used — Witnessed by —

Checked for shut off @ — (AM) (PM) Date —

Method used — Witnessed by —

★ Remarks: Ran 30 jts 8 5/8" 1125' DF 1110' GL circulated Cem
estimate 90 Sk Cem to pt.