

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>C. E. LaRue & B. N. Muncy Jr.</i>		Lease <i>P.V. State</i>		Well # <i>1</i>	
Location of Well	Unit <i>9925 43cc P</i>	Section <i>16</i>	Township <i>19</i>	Range <i>26</i>	County <i>Eddy</i>
Drilling Contractor <i>CO Tools</i>	Type of Equipment <i>Rotary to start approx. 7-28-76</i>				

* *Witness*

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>13 3/4"</i>	<i>10 3/4"</i>	<i>36</i>		<i>350</i>	<i>75 circ.</i>
<i>9 7/8"</i>	<i>7"</i>	<i>23</i>		<i>920</i>	<i>275 circ.</i>
<i>6 1/8"</i>	<i>4 1/2"</i>	<i>10 1/2</i>		<i>2100</i>	<i>175 circ.</i>

Casing Data:

Int
~~Surface~~ *23* joints of *7* inch *20*th # Grade *API 155*
(Approved) (~~Rejected~~)

Inspected by *Nick Tinker* date *7-31-76*

Cementing Program

Size of hole *9 7/8* Size of Casing *7" OD* Sacks cement required *450*

Type of Shoe used *Guide* Float collar used *yes* Btm 3 jts welded *yes*

TD of hole *920'* Set *919* Feet of *7* Inch *20*th # Grade *155*

New-used csg. @ *912* ft with *450* sacks neat cement around shoe

+ *1/4* # per sack cement *290 cc* additives *cellulose* *5# Saline* *per sack cement*

Plug down @ *530* (AM) (PM) Date *July 31, 1976*

Cement circulated *No* No. of Sacks *—*

Cemented by *Dowell* Witnessed by *Nick Tinker*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *After bumping plug top of cement backed about 25' of reaching surface so ready mixed to surface*

5-3-76 As per spec. 400 SX Class C 290cc 1/4 # Cellulose + 5# Saline + 50cc S. 290cc

Temp survey 76C-79C - ran 1' to 790 + Cement w/ 50 SX - 1000 S.M. Tag @ 651
Circulated to surface w/ 200 SX