

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Roger C. Hanks</u>		Lease <u>Dee State Com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>I</u>	Section <u>36</u>	Township <u>19</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor <u>Moran Bros.</u>			Type of Equipment <u>Rotary to start upon approval</u>		

* witness APPROVED CASING PROGRAM 8-3-76

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48</u>		<u>415</u>	<u>300 circ</u>
<u>11"</u>	<u>8 5/8"</u>	<u>24</u>		<u>1125</u>	<u>600 circ.</u>
<u>7 7/8"</u>	<u>5 1/2"</u>	<u>20</u>		<u>7950</u>	<u>200</u>

Casing Data:

Surface 29 joints of 8 5/8 inch 24 # Grade API New K-55
(Approved) (Rejected)

Inspected by Salan Mermis date 9-27-76

Cementing Program

Size of hole 12 1/4" Size of Casing 8 5/8 Sacks cement required 750/sx

Type of Shoe used Texas Float collar used Insert Btm 2 jts welded Thread Lock

TD of hole 1115' K13 Set 1103' PL Feet of 8 5/8 inch 24 # Grade K-55

New-used csg. @ 1103' GL with 150 sacks neat cement around shoe (Class C 2% cc)

+ 200 / sax Thix-set 4# Gilschite 2% cc 400/sx Howe White 5# Gilschite 4# Flocite 2% cc

Plug down @ 4:45 (AM) (PM) Date 9-27-76

Cement circulated No No. of Sacks None

Cemented by Halliburton Witnessed by Salan Mermis

Temp. Survey ran @ 11:30 (AM) (PM) Date 9-27-76 top cement @ 500'

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Water 475-531, 779-850 Lost Zone 525, Back to 550-470

Ran 1" to 480' Cnt 35/sx Class C 4% cc PD 1:15 AM 9-28-76

" 1" to 445' " 35/sx " " " " PD 4:30 AM "

" 1" to 440' " 50/sx " " " " PD 7:45 AM "

" 1" to 310' " 90/sx Class C 2% cc PD 10:15 AM " Circ 5/sx