

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Monsanto Co.</u>		Lease <u>Albert Stab Com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>F</u> <u>1980 NW</u>	Section <u>32</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>Cactus Drilling Co.</u>		Type of Equipment <u>Rotary & start approx 8-1-77</u>		

APPROVED CASING PROGRAM

* witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8"</u>	<u>48</u>		<u>400</u>	<u>500 c/c</u>
<u>12 1/4</u>	<u>9 5/8</u>	<u>36</u>		<u>1400</u>	<u>800 c/c</u>
<u>8 3/4</u>	<u>5 1/2</u>	<u>20</u>		<u>9600</u>	<u>800</u>

Casing Data:

Surface 33 joints of 9 5/8 inch 36 # Grade API New H-40
(Approved) (Rejected)

Inspected by Selen Mearis date 8-29-77

Cementing Program

Size of hole 12 1/4" Size of Casing 9 5/8" Sacks cement required 7.50/sx

Type of Shoe used Guide Float collar used Yes Btm 2 jts welded Thread Lock

TD of hole 1400' KB Set 1384' GL Feet of 9 5/8 Inch 36 # Grade H-40

New-used csg. @ 1384' GL with 2cc sacks neat cement around shoe Class 22 cc
+ 550/sax Dowell Lite additives 5# Kelite 2# Cella Flake 2% cc

Plug down @ 10:00 (AM) (PM) Date 8-29-77

Cement circulated Yes No. of Sacks 7.50/sx

Cemented by Dowell Witnessed by Selen Mearis

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Water 915-80