

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Petroleum Corp.</i>		Lease <i>Ross "12"</i>		Well # <i>1</i>	
Location of Well	Unit <i>F 1980NW</i>	Section <i>28</i>	Township <i>19</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor	<i>moranco</i>		Type of Equipment <i>Rotary</i>		

APPROVED CASING PROGRAM

* witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>13 7/8"</i>	<i>48</i>		<i>350</i>	<i>Circ</i>
<i>12 1/4"</i>	<i>8 7/8"</i>	<i>24</i>		<i>1200</i>	<i>Circ.</i>
<i>7 7/8"</i>	<i>4 1/2 or 5 1/2</i>			<i>9600</i>	<i>200</i>

Casing Data:

Surface *26* joints of *8 5/8* inch *24* # Grade *J-55*

(Approved) (Rejected)

Inspected by *M.S.* date *3/13/78*

Cementing Program

Size of hole *12 1/4* Size of Casing *8 5/8* Sacks cement required *600*

Type of Shoe used *guide* Float collar used *insert* Btm 3 jts welded *yes*

TD of hole *1180'* Set *1180'* Feet of *8 5/8* Inch *24* # Grade *J-55*

New-used csg. @ *1180'* with *150* sacks neat cement around shoe

+ *450* sack *50-50* additives *470 gals. Spicers K Kelite 1/4 gal. 290 cc*

Plug down @ *12:00* (AM) (PM) Date *3/13/78*

Cement circulated *yes* No. of Sacks *70*

Cemented by *Dowell* Witnessed by *Mike Stull*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *Water sample 933-1045' Set 1 cement @ 920' 2 cementizers @ 920' + 1180'*