

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 120
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Phoenix Resources Co.</i>		Lease <i>Gardner Draw Unit</i>		Well # <i>2</i>	
Location of Well	Unit <i>800² 1980e</i>	Section <i>19</i>	Township <i>19</i>	Range <i>21</i>	County <i>Eddy</i>
Drilling Contractor	<i>Cactus</i>		Type of Equipment <i>Rotary to start approx. 5-10-78</i>		

* witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2</i>	<i>13 7/8</i>	<i>48</i>		<i>300</i>	<i>300 circ.</i>
<i>12 1/4</i>	<i>8 5/8</i>	<i>24+32</i>		<i>1800</i>	<i>1000⁺ circ.</i>
<i>7 7/8</i>	<i>4 1/2</i>	<i>11.6</i>		<i>7300</i>	<i>500</i>

Casing Data:

Enter.

Surface joints of *8 5/8* inch *24* # Grade *K-55*

(Approved) (Rejected)

Inspected by *M.S.* date *5/24/78*

Cementing Program

Size of hole *12 1/4* Size of Casing *8 5/8* Sacks cement required *1250*

Type of Shoe used *guide* Float collar used *+ float* Btm 3 jts welded *yes*

TD of hole *1755'* Set *1755* Feet of *8 5/8* Inch *24* # Grade *K-55*

New-used csg. @ *1755* with *200* sacks neat cement around shoe

+ *400* sax *RFC* additives *1/4 pd celoflate 1 1/2 gilsonite*

Plug down @ *11:00* (AM) (PM) Date *5/24/78*

Cement circulated *No* No. of Sacks

Cemented by *Dowell* Witnessed by *Mark Stubblefield*

Temp. Survey ran @ *200* (AM) (PM) Date *5/25/78* top cement @ *1030'*

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *+ 650 sxs class C 6 5/8 size per 3 additives 470 gels 1/4 cel.*

12 1/2 pd gilsonite per sack.

Lost Drly. Break 749'
Lost circulation 400'