

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Amoco Prod. Co.</i>		Lease <i>State GF</i>		Well # <i>1</i>	
Location of Well	Unit <i>1980s+e</i>	Section <i>24</i>	Township <i>19</i>	Range <i>27</i>	County <i>Eddy</i>
Drilling Contractor	<i>Landis Rig 3</i>		Type of Equipment <i>Rotary to start approx 8-15-78</i>		

APPROVED CASING PROGRAM

\* *witness*

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2</i>	<i>13 3/8"</i>	<i>48</i>		<i>400</i>	<i>circ.</i>
<i>12 1/4</i>	<i>9 5/8"</i>	<i>36</i>		<i>2500</i>	<i>circ.</i>
<i>8 3/4</i>	<i>5 1/2</i>	<i>15.5+17</i>		<i>11000</i>	

Casing Data:

*Inter.*  
Surface *63* joints of *9 5/8* inch *36* # Grade *K-55*

*yes* (Approved) (Rejected)

Inspected by *B.W. Weaver* date *8-24-78*

Cementing Program

Size of hole *12 1/4* Size of Casing *9 5/8* Sacks cement required *800*

Type of Shoe used *guide* Float collar used *yes* Btm 3 jts welded *yes*

TD of hole *2495'* Set *2495'* Feet of *9 5/8* Inch *36* # Grade *K-55*

New-used csg. @ *2495'* with *200 2 1/2* sacks neat cement around shoe

+ *600* sax *Hall. Lite* additives *5# gilsonite, 1/4# flocc, 8# salt*

Plug down @ *2455* (AM) (PM) Date *8/25/78*

Cement circulated *yes* No. of Sacks *40 sx*

Cemented by *Halliburton* Witnessed by *Mike Stubbfield*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks:

*Last daily break @ 863'*