

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yatic Ltr. Corp.</u>		Lease <u>Dresswood 8D State</u>		Well # <u>3</u>	
Location of Well	Unit <u>D</u> <u>980W</u>	Section <u>6</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>La Rue Drilling Co.</u>		Type of Equipment <u>Rotary to start</u> <u>10-18-79</u>		

* witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>15"</u>	<u>10 3/4"</u>	<u>32.75</u>		<u>320</u>	<u>275 cum</u>
<u>9 5/8"</u>	<u>7"</u>	<u>20</u>		<u>1000</u>	<u>500 "</u>
<u>6 1/4"</u>	<u>4 1/2"</u>	<u>9.5</u>		<u>3150</u>	<u>200 "</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 9 1/2 Size of Casing 7" Sacks cement required _____

Type of Shoe used Guide Float collar used Insert Btm 3 jts welded yes

TD of hole 960 Set 980 Feet of 7 Inch 23+20 # Grade J-40

New-~~used~~ csg. @ 980 with 100 C sacks neat cement around shoe

+ 150 BFC sax + 300 5X 50+50 Pbs additives 6% Jel 1/4 Flo Seal

Plug down @ 7:00 (AM) (PM) Date 10-19-79

Cement circulated None No. of Sacks _____

Cemented by Dowell Witnessed by B.W. Weaver

Temp. Survey ran @ 12:30 (AM) (PM) Date 10-19-79 top cement @ 660

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Loss Circulation zone @ 690 Ran 1" to 640 ft cemented with

25 SX 4% cc Tagged @ 600

2nd Stage 50 SX @ 600 Tagged Top @ 475

3rd Stage 120 SX @ 475 to Surface