

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Southland Loyalty Co.</i>		Lease <i>State 14A Com.</i>		Well # <i>1</i>	
Location of Well	Unit <i>1325 2303 c</i>	Section <i>14</i>	Township <i>19</i>	Range <i>29</i>	County <i>Eddy</i>
Drilling Contractor <i>Hondo Rigs</i>			Type of Equipment <i>Rotary to start 10-23-79</i>		

* *Witness*

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>24"</i>	<i>20"</i>	<i>94</i>		<i>250</i>	<i>350 air</i>
<i>17 1/2"</i>	<i>13 3/8"</i>	<i>48</i>		<i>1350</i>	<i>1000 "</i>
<i>11"</i>	<i>8 5/8"</i>	<i>24</i>		<i>2800</i>	<i>1200 "</i>
<i>7 7/8"</i>	<i>4 1/2"</i>	<i>11.6</i>		<i>11850</i>	<i>800</i>

Casing Data:

Surface _____ joints of *1 3/8* inch *48* # Grade *H-40*
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole *17 1/2* Size of Casing *1 3/8* Sacks cement required _____

Type of Shoe used *guide* Float collar used *yes* Btm *2* jts welded *yes*

TD of hole *1356'* Set *1350'* Feet of *1 3/8* Inch *48* # Grade *H-40*

New-used csg. @ *1350'* with *300 3/4* sacks neat cement around shoe

+ *1100* sack *Hall's* additives *40 gal, 6# gilsonite, 1/4# flocc, 20cc*

Plug down @ *7:00* (AM) (PM) Date *10/31/79*

Cement circulated *yes* No. of Sacks *140 ex*

Cemented by *Halliburton* Witnessed by *Mike Sturfield*

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____

centralizers @ 1350'-1225', 600'-40'

Lost daily break @ 1238'
Set 385'-1238'