

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Gates Lbr. Corp.</u>		Lease <u>Quinnwood 60 State</u>		Well # <u>7</u>	
Location of Well	Unit <u>80N 330W</u>	Section <u>6</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>Cactus Drilling Co.</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>15"</u>	<u>10 3/4"</u>	<u>37.75</u>		<u>320</u>	<u>275 cu.</u>
<u>9 7/8"</u>	<u>7"</u>	<u>20</u>		<u>1000</u>	<u>500 "</u>
<u>6 1/4"</u>	<u>4 1/2"</u>	<u>9.5</u>		<u>3150</u>	<u>200 "</u>

Casing Data:

Int
Surface 25 joints of 7 inch 20 # Grade J-SS
✓ (Approved) (Rejected)

Inspected by mw date 4/5/80

Cementing Program

Size of hole 9 7/8 Size of Casing 7 Sacks cement required 600

Type of Shoe used Guide Float collar used Insert Btm 3 jts welded Yes

TD of hole 982 Set 1007 Feet of 7 Inch 20 # Grade J-SS

New-used csg. @ 982 with 150 sacks neat cement around shoe

+ 450 sax 65/35 Poz additives 2 # Kelite - 1/4" #16 476 D-20 Barlonide - 3724

Plug down @ 1:45 (AM) (PM) Date 4/6/80

Cement circulated Yes No. of Sacks 35

Cemented by Dowell Witnessed by MW

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Btm Breck @ 882'