

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 110
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Petr Corp</u>		Lease <u>Rough N</u>		Well # <u>1</u>	
Location of Well	Unit <u>A</u>	Section <u>14</u>	Township <u>19</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	<u>L + m Drilling</u>		Type of Equipment <u>Rotary</u>		

* witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
15	10 3/4	32.3		363'	3155x Circ
* 9 5/8	7	20		225'	3755x Circ
6 1/4	4 1/2	9.5		3000'	2755x

Casing Data:

Surface joints of 7 inch 20 # Grade J-55
(Approved) (Rejected)

Inspected by M. S. date 5/7/80

Cementing Program

Size of hole 9 1/2 Size of Casing 7 Sacks cement required

Type of Shoe used guide Float collar used insert Btm 3 jts welded yes

TD of hole 920' Set 919' Feet of 7 inch 20 # Grade J-55

New used csg. @ 919' with 150 2% sacks neat cement around shoe
+ 250 sax C additives 3%

Plug down @ 9:45 (AM) (PM) Date 5/8/80

Cement circulated No No. of Sacks -0-

Cemented by Dowell Witnessed by Mike Stubbfield

Temp. Survey ran @ 2:45 (AM) (PM) Date 5/8/80 top cement @ 260'

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: + 450 6 5/8 per. (1/4" celoflakes, 8# kelite, 4% D²⁰ gel, 3% cc)

Drisket @ 415' lost circ. @ 368'
lost dily break @ 755'

1 Run 1" tagged TOC @ 260'

Pumped 90sx cement.

Cement circulated.