

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Amoco Production Co</u>		Lease <u>State IL Com</u>		Well # <u>1</u>	
Location of Well	Unit <u>192nd 6</u>	Section <u>3</u>	Township <u>19</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	Type of Equipment <u>Rohrer</u>				

* witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8</u>	<u>48 #</u>		<u>400'</u>	<u>Circ</u>
* <u>12 1/4</u>	<u>9 5/8</u>	<u>36 #</u>		<u>1500'</u>	<u>Circ</u>
<u>8 3/4</u>	<u>5 1/2</u>	<u>15.5 # 17-20 #</u>		<u>9000</u>	<u>Btm 9 5/8</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4" Size of Casing 9 5/8" Sacks cement required _____

Type of Shoe used guide Float collar used yes Btm 3 jts welded yes

TD of hole 1500' Set 1500' Feet of 9 5/8" Inch 36 # Grade J-SS

New used csg. @ 1500' with 200 sacks neat cement around shoe
+ 750 sack BJ Hite additives + 400 sack Thickset

Plug down @ 11:00 (AM) (PM) Date 6/8/80

Cement circulated No No. of Sacks -0-

Cemented by BJ Hughes Witnessed by B.W. Weaver

Temp. Survey ran @ 5:00 (AM) (PM) Date 6/8/80 top cement @ 435'

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____

lost circ. @ 446'
lost dry break @ 860'

1 Run 1" Tagged TOC @ 462'

Pumped 25 sx C 270 cc

11:46 AM 2 Run 1" Tagged TOC @ 462'

Pumped 25 sx C 270 cc.

1:40 AM 3 Run 1" Tagged TOC @ 462'

Pumped 25 sx C 270 cc

3:50 AM 4 Run 1" Tagged TOC @ 462'

Pumped 25 sx C 270 cc

6:15 AM 5 Run 1" Tagged TOC @ 462'

Pumped 25 sx C 270 cc.

10:05 AM 6. Run 1" Tagged TOC @ 462'

Dumped 1/2 yd pea gravel

Pumped 50 sx surefill (10# gilsonite, 270 cc)

7 Run 1" Tagged TOC @ 240'

Pumped 16 sx C 270 cc.

cement circulated. OK mixer still open