

OIL CONSERVATION DIVISION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

|                                  |                        |                             |                                  |             |                |
|----------------------------------|------------------------|-----------------------------|----------------------------------|-------------|----------------|
| Operator<br>Yates Petroleum Corp |                        | Lease<br>Glass-Kincaid '05" |                                  |             | Well #<br>1    |
| Location of Well                 | Unit<br>330N<br>330W D | Section<br>7                | Township<br>19                   | Range<br>25 | County<br>Eddy |
| Drilling Contractor              | Artesia Fishing Tool   |                             | Type of Equipment<br>ASAP Rotary |             |                |

\* Witness

APPROVED CASING PROGRAM

| Size of Hole | Size of Casing | Weight Per Foot | New or Used | Depth                   | Sacks Cement |
|--------------|----------------|-----------------|-------------|-------------------------|--------------|
| 15"          | 10 3/4"        | 32.75#          |             | 350'<br><del>310'</del> | 250 SX Circ  |
| * 9 1/2"     | 7"             | 20#             |             | 970'                    | 500 SX Circ  |
| 6 1/4"       | 4 1/2"         | 9.5#            |             | 3100'                   | 250 SX Circ  |

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch # Grade \_\_\_\_\_  
(Approved) (Rejected)

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 9 1/2" Size of Casing 7" Sacks cement required \_\_\_\_\_

Type of Shoe used guide Float collar used insert Btm 3 jts welded yes

TD of hole 953' Set 953' Feet of 7" Inch 23 # Grade J-55

New-used csg. @ 953' with 150 2% cc sacks neat cement around shoe  
+ 200 sax c additives 3% cc

Plug down @ 12:30 (AM) (PM) Date 4/11/81

Cement circulated No No. of Sacks -0-

Cemented by Dowell Witnessed by Mike Stullfield

Temp. Survey ran @ 5:30 (AM) (PM) Date 4/11/81 top cement @ 640'

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: +800 sx 65/35 poz. (4% ogel, 8# Kolite, 1/4# caloflakes, 3% cc)

last circulation @ 636'

last dry break @ 853'

No centralizers

1 Run 1" Tagged TOC @ 498'  
Pumped 25 sx c 4% cc 10# 20/40 sand/sx

2 Run 1" Tagged TOC @ 458'  
Pumped 50 sx c 4% cc 10# 20/40 sand/sx

3 Run 1" Tagged TOC @ 360'  
Pumped 100 sx c 4% cc 10# sand/sx.  
Cement circulated to surface. OK